

# $\mu$ -X360J

## Residual Stress Reference Specimen (Option)

Residual Stress Reference Specimen for customer's inspection purpose.

For daily check, start-up inspection

For operation error check, instrumental error check

For machine variation check

**The specimen should be helpful to solve the problem.**

### Line-up



	High	Medium	Low	Very low
Residual stress	-1600MPa	-800MPa	-400MPa	>-50MPa
Material	SCM420 (Gear steel)	SUP9 (Spring steel)	SM490 (Welding steel)	SCM420
Size	W40×D40×H20mm			
Measurement area	Φ20mm	Φ19mm	Φ20mm	SCM420 : φ20mm
contains	Residual Stress Reference Specimen (wrapped with anti-rust paper), Datasheet			

\* Size may change without notification.

\* Please contact us, if you have special request of the stress value, materials, etc.

\* manufactured by SINTOKOGIO, LTD.

7000-35 Nakagawa, Hosoe-cho, Hamana-ku,  
Hamamatsu-city, Shizuoka 4311304 JAPAN  
TEL+81(0)535223611 FAX +81(0)535223666  
E-mail: [sales@pulstec.co.jp](mailto:sales@pulstec.co.jp)



**Pulstec Industrial Co., Ltd.**

URL: <https://www.pulstec.co.jp/>